

## Aura STARK

Enamel anticorrosive 3 in 1



- ✓ Apply directly to rust
- ✓ No priming required
- ✓ Ideal for protecting wood and metal



Description	
Properties	<p>Alkyd enamel 3 in 1 for exterior and interior use.</p> <ul style="list-style-type: none"> <li>✓ Does not require preliminary priming.</li> <li>✓ Ideal for protecting wood and metal.</li> <li>✓ Forms a strong, weather-resistant, decorative coating.</li> <li>✓ Provides long-term protection.</li> <li>✓ Can be applied to ferrous metals with traces of tightly adhering rust and scale.</li> <li>✓ Provides enhanced protection of metal surfaces against corrosion, weather and mechanical influences.</li> <li>✓ Prevents spread of sub-film corrosion.</li> <li>✓ Ready for use.</li> <li>✓ Long-lasting, weather-resistant, resistant to mechanical stress.</li> <li>✓ Forms a glossy film.</li> <li>✓ Good adhesion (adhesive force) to the surface to be painted.</li> <li>✓ High hiding power.</li> </ul>
Appointment	Enamel 3 in 1 for exterior and interior use. It is intended for the protection of metal surfaces with the remnants of tightly adhering rust with a thickness of up to 100 microns and scale.
Types of surfaces for application.	It is used for industrial structures and equipment, agricultural machinery, railway transport, pipelines, tanks, household building structures, garages, gates, forged products, fences, gratings, garden metal furniture, etc. It can also be used for painting wooden and concrete surfaces.
Quality standards	
Specifications	

Surface preparation.	Before carrying out painting work, the surface must be carefully prepared: remove old peeling paint coatings, as well as loose and peeling rust from the surface. Smooth surface must be matted with sandpaper. The surface must be dry, free from grease stains and dust. The moisture content of wood should not exceed 18%, and the humidity of concrete should not exceed 4%.
Application	Before use, mix the enamel, if necessary, dilute with white spirit or solvent no more than 10% by weight of enamel. It is not permissible to dilute the enamel with other solvents or mix the enamel with other paints and varnishes. Apply enamel at surface, enamel and air temperature not lower than + 5 ° C and relative air humidity not more than 70%. To create an optimal reliable protective coating, enamel is recommended to be applied on 3 surfaces for external surfaces and 2 layers on internal surfaces. Each subsequent layer is applied after the previous one has completely dried.
Color	Ready-made colors according to the catalog.
Consumption	120-150 g/m <sup>2</sup> for single coat application. The flow rate is affected by the type of surface, its preparation and the method of applying enamel.
Drying time	The drying time of each layer at a temperature of + 20 ° C and a relative humidity of 65% is at least 8 hours. The drying speed is affected by temperature, relative humidity and film thickness.
Tools	Brush, roller or sprayer.
Tools cleaning	Rinse immediately with white spirit and then warm water with detergent immediately after use. The dried enamel is cleaned mechanically.
Composition	Suspension of pigments and fillers in alkyd varnish with the addition of white spirit and functional additives.
<b>Additional Information</b>	
Frost resistance	Frost resistant.
Warranty period of storage	The warranty shelf life is 24 months from the date indicated on the package.
Storage conditions	Store and transport in the original hermetically sealed container, protecting from moisture and direct sunlight. Not afraid of frost. Storage at low temperatures is possible.
Precautionary measures	Harmful, if swallowed, may cause lung damage. Keep out of the reach of children. Avoid breathing solvent vapor. Avoid contact with skin. Work in a respirator, in a well-ventilated area. <b>Keep away from fire!</b>
Disposal	Do not pour into drains, water, or soil. Dispose of closed containers with dry product residues in organized collection points for household waste.
Weight	0,7 kg - 2,0 kg
<p>The above, up-to-date information in the Technical Description is based on our practical experience, as well as on our laboratory testing of products and is provided in all the volume available to us. The presented information can be used as recommendations when choosing products and working methods for its application. The manufacturer guarantees the conformity of products with the specified technical specifications only in case of compliance with the rules of transportation, storage, preparation, preparation, use, operation, which are given in this Technical Description. The manufacturer does not have the ability to foresee and control all conditions for the use of products, as well as various factors that affect its use and further operation. Taking into account the variety of materials of surfaces and specific conditions of objects on which products are used, the Consumer should carefully check the products for their suitability for a particular object, taking into account all possible conditions of its use not specified in this Technical Description. The presented information does not relieve the Consumer from responsibility for the quality of work. In case of non-compliance by the Consumer with the requirements of the Technical Description (Operating Instructions), the use of products for other purposes, the Manufacturer shall not be legally responsible for any damage caused to the Consumer. The manufacturer, on the basis of new product knowledge, reserves the right to amend the Technical Description in the prescribed manner. The text of the new edition of the Technical Description is placed by the Manufacturer on the website <a href="http://www.eskaro.ua">www.eskaro.ua</a> with the date of introduction and the number of the new edition of the Technical Description. When a new edition of this Technical Description is released, the previous edition loses its force and is removed by the Manufacturer from the site. Additional information can be obtained from the representative of the Manufacturer or on the website <a href="http://www.eskaro.ua">www.eskaro.ua</a></p>	
Revision of Technical Description №01 as of December 4th, 2019.	