

Marine Lakk 90

Varnish for wooden boats





- ✓ Gloss
- ✓ Weather-resistant
- ✓ Resistant to sea water exposure
- ✓ Protects the surface from mechanical damage



Description	
Properties	<p>Urethane alkyd yacht varnish for interior and exterior use.</p> <ul style="list-style-type: none"> ✓ Provides a hard semi-matt coating resistant to cracking. ✓ Has very high abrasion resistance. ✓ Has excellent resistance to washing and exposure to household chemicals and salty water. ✓ The UV filter prevents wood from discoloration when exposed to sunlight. ✓ Suitable for decorative varnishing. ✓ High weather resistance even in adverse climatic conditions. ✓ Enhances the natural beauty of the wood. ✓ Contains highly purified and low aromatic solvents. <p>Maximum permissible EU VOC content for the product (subcat i) 500 g/L. Maximum VOC content in the product <500 g/L.</p> <p>Gloss:</p> <ul style="list-style-type: none"> ✓ Gloss (approximately 90) in accordance with ISO 2813.
Purpose	<p>Decorative and protective varnish finishing of indoor and outdoor wooden surfaces. Wooden boats, yachts and motor boats, including decks, cabins etc. Suitable for varnishing window frames, doors, parquet and wooden floors, stairs, furniture and interior elements, garden furniture etc. The varnish is not meant for steam rooms.</p>
Type of surfaces to be treated	New or previously varnished wooden surfaces.
Quality standards and labels	<ul style="list-style-type: none"> ✓ ISO 11 998 [Paints and varnishes -- Determination of wet-scrub resistance and cleanability of coatings], ISO 2813 [Paints and varnishes -- Determination of specular gloss of non-metallic paint

	<p>films at 20 degrees, 60 degrees and 85 degrees] – techniques for measuring gloss and wear resistance parameters</p> <ul style="list-style-type: none"> ✓ VOC (volatile organic compounds) – content in accordance with the European Union directive 2004/42/CE ✓ Product and service quality is guaranteed by the quality, environmental protection, occupational health and safety management system in accordance with standards ISO 9001:2015; ISO 14001:2015 and OHSAS 18001:2007.
Product specifications	
Surface preparation before treatment	<p>Wood moisture content must not exceed 20%. Perform application at the temperature between 5 °C and 25 °C, relative humidity between 40% and 75%, and varnish temperature between 18 °C and 25 °C. Finish outdoor surfaces so that the varnish surface can dry before the evening dew falls. Do not perform the application in direct sunlight, at high temperatures and in case of exposure to draughts. Clean the surface from dirt, grease, oils, silicone or wax. Use White-Spirit solvent to wipe new hardwood surfaces (oak, beech).</p> <p>Dampen rough surfaces, using a spray bottle; let them dry and sand off the fibres of wood raised by dampening. Before finishing previously varnished surfaces, we recommend making a varnish swatch on a small surface patch to check that the materials are compatible.</p> <p>Previously varnished surfaces do not require preliminary priming; they need to be thoroughly cleaned from old peeling varnish, carefully sanded and cleaned from dust.</p> <p>For priming new non-painted surfaces, dilute the varnish with White-Spirit in the ratio of 5:1. Treat the surfaces exposed to the weather impact with the Biostop agent and prime them with diluted varnish.</p>
Application	<p>Before application and in the process of working, stir the varnish thoroughly but carefully (to make sure you do not cause air bubbles to form in it). Stirring ensures that the gloss of the varnish coating will be even when it dries.</p> <p>Apply 2 coats of varnish on the surface along the grain of the wood or in the direction of the light from the window.</p> <p>The number of varnish coats depends on the porosity of the wood and the instrument you use. Sand the surface with fine sandpaper (120–150) and remove the dust before applying each following coat on the new surface that has not been previously painted.</p> <p>Apply finishing varnish on previously varnished surfaces in thin coats without priming. Only apply each following varnish coat after the previous coat has fully dried.</p> <p>Use tinted varnish for the first coat only. Apply non-tinted varnish as the last coat.</p> <p>You can use the Balance decorative wood protecting coating (in supplied colours or tinted) as the first coat for tinting.</p> <p>To check the tint, we recommend making a varnish swatch on a separate board as the final tint of the coating depends on the species of wood (exotic or unknown wood species can change their colour or get stains), the initial hue and the number of varnish coats.</p> <p>Hardwood species should be used for surfaces exposed to mechanical impacts or requiring high durability. Softwood species (spruce, pine, lime tree etc.) are likely to suffer deformation even after varnishing.</p> <p>Make sure the working area is well-ventilated, but with no draughts that can cause surface defects. In a dry and hot climate, turn down the ventilation to prevent the paint from drying too fast and avoid lap marks.</p>
Care for the treated surface	<p>Avoid using detergents or vigorously cleaning freshly varnished surfaces because it takes the coating two weeks to reach its peak hardness and durability after the varnish is applied. If necessary, wipe lightly with soft damp cloth during this period. In approximately 2 weeks after varnishing, the dried coating can be cleaned with neutral (pH 6–8) detergents and a soft sponge or cloth. Rinse the surface thoroughly with clean water and dry it after cleaning.</p> <p>Rinse the surface thoroughly with clean water after cleaning and dry it.</p>
Colour	Colourless
Tinting	Machine tinting according to the Eskarocolor system (Base EC)
Consumption	8-12 m ² /L..
Thinner	White-Spirit.
Drying time	<p>Dust-free drying time: 4 hours; at the temperature of +20 °C and the relative humidity of 65%, the surface is fully dry in 18 hours.</p> <p>The previously sanded surface can be varnished again in 24 hours .</p>
Tools	<p>Brush, padded varnish applicator, spray gun with 0.009–0.013" nozzle. When applied with a spray gun, the varnish can be diluted with White Spirit in the amount of up to 10% of the varnish volume. When applied with an applicator, little of the varnish is absorbed by the wood, which results in its lighter colour. The blade of the applicator must be flexible enough to follow the roughness of the floor and sufficiently sharp for the applicator to act as a knife and smooth down protruding wood fibres. The brush used for varnish application must be wide with well-fastened natural or synthetic bristles.</p>
Tool cleaning	Wash with White-Spirit after completing work.
Additional information	
Frost resistance	Frost-resistant.
Min shelf life	5 years.
Storage conditions	<p>Store and transport in undamaged containers at the temperature up to +30°C. Store in a well-ventilated place. Keep cool. Keep container tightly closed. Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking. Store locked up.</p>

Safety precautions	  <p>Warning. Flammable liquid and vapour. May cause an allergic skin reaction. May cause drowsiness or dizziness. Contains: hydrocarbons, C9-C11,n-alkenes, iso-alkenes, cyclics, <2% aromatics; Cobalt bis(2-ethylhexanoate) (CAS: 136-52-7). Repeated exposure may cause skin dryness or cracking. Contains 4,5-dichloro-2-octyl-2H-isothiazol-3-one, Butan-2-one oxime , octabenzone. May produce an allergic reaction. Wear protective gloves/protective clothing/eye protection/face protection. IF ON SKIN: Wash with plenty of water. Use only outdoors or in a well-ventilated area. Avoid breathing dust/fume/gas/mist/vapours/spray. IF INHALED: Remove person to fresh air and keep comfortable for breathing. Call a POISON CENTER/doctor if you feel unwell. If medical advice is needed, have product container or label at hand. Keep out of reach of children. In case of fire: Use ABC powder extinguisher to extinguish.</p>
Waste treatment	<p>Avoid release to the environment. Dispose of the contents/containers in accordance with the current legislation on waste treatment.</p> <p>Waste treatment methods: code 08 01 11* - Waste paint and varnish containing organic solvents or other dangerous substances; waste class (Regulation (EU) No 1357/2014): dangerous.</p>
Density	0,9 kg/L.
Volume/weight	0.95 L – 2.4 L – 9.5 L
<p>The information concerning the product is based on the results of laboratory tests and practical use of the product depending on the location and conditions of its use. As the manufacturer, we guarantee the quality of the product and provide the best recommendations for its appropriate application. As the manufacturer, we cannot control the conditions and circumstances of product transportation, storage and application and numerous other factors that affect its use. Thus, we shall not bear responsibility for the damage caused by ignoring the instructions for use or transportation, by noncompliance with storage conditions and timeframes or by inappropriate application of the product. The manufacturer reserves the right to alter product information at their discretion without prior notice. For additional information, please contact us: http://eskaro.ua/kontakty_ukr/</p>	