



Aura Luxpro Parkett Elit Matt

Decorative and protective varnish for parquet

- ✓ Semi-matt
- ✓ Polyurethane
- ✓ Water based
- ✓ Firm and elastic
- ✓ Resistant to abrasion



Description	
Properties	<p>Semi-matt parquet polyurethane water-based varnish.</p> <ul style="list-style-type: none"> ✓ Emphasizes wood structure. ✓ Perfectly protects the surface from damage, contamination (household pollutants) and moisture penetration. ✓ Withstands intense abrasive mechanical stress. ✓ Resistant to most household chemicals. ✓ Forms a solid and elastic transparent colorless coating. ✓ Does not change the color of wood. ✓ Does not turn yellow. ✓ Without bad smell. ✓ It spreads well on the surface, dries quickly. ✓ Has good adhesion to various types of wood. ✓ VOC content (volatile organic compounds) complies with European Union Directive 2004/42 / EC. ✓ Withstands repeated wet cleaning using neutral, non-abrasive detergents. ✓ Do not use hard brushes and sponges, or organic solvents for cleaning. ✓ When installing furniture for legs, use special pads. <p>The maximum allowable VOC content for a product (subgroup e) is 130 g / L (2010). Max. VOC content of the product <100 g / L.</p> <ul style="list-style-type: none"> • Hardness: 100 (Koenig method, 7 days, ISO 1522). • Resistance to abrasion: <15 mg (Taber Abraser / cs-10/1000 cycle / 1000 grams).
Appointment	Decorative-protective polyurethane semi-matt water-based varnish for parquet. For new or previously painted surfaces. For indoor use in residential and public areas with normal and high

	humidity. For "floating" floors and heated floors. The varnish is not intended for a bath (sauna).
Types of surfaces for application	For wooden parquet: firmly glued mosaic, piece, end, sheet (plate). For wooden floors, wooden staircases and railings. The varnish can be used for all wooden interior elements (tabletops, furniture, windows, doors, etc.), as well as wood materials (fiberboard, particleboard, Fiberboard, Oriented Chipboard, cork, etc.).
Quality standards	
Specifications	
Surface preparation	<p>Surface: dry, durable, clean, fat free, dust free. The moisture content of wood is less than 12%. New surface (or previously varnished surface with removal of the old varnish coating): For maximum adhesion and durability of a varnish coating it is recommended to process new wood or the wood which is completely cleared of old coatings (varnish, paint, wax, oil, silicone, parquet care products, etc.). A layer of wood, soaked in oil, completely remove (recycle) to the depth of penetration of the oil. Degrease the treated surfaces of tropical varieties of wood, solid wood (oak, beech) and tarry sticky wood. Moisten rough wood slightly with water and, after drying, remove the raised pile by grinding. The first sanding of wood is carried out with rough sandpaper. When grinding, smooth the surface as much as possible. Finish grinding before priming (or before applying tinting material) with fine emery paper (240), remove dust. Prime the prepared surface with one coat of primer. For priming, use PARKETT ELIT varnish, diluted with water by 10-15% with a flow rate of 10-15 m² / l. For priming, a filler (acrylic or nitrocellulose) for wood can be used. Priming tool: varnish roller (or brush). After priming (after 4 hours), sand the dried surface with fine emery paper (240), removing the raised pile. Remove dust. Before applying varnish, check in a small area its compatibility with the surface of the treated wood. Some exotic and hardwoods may experience a sharp change in color. In all cases, remove dust from the work surface and from the surrounding elements with a vacuum cleaner, and then with a clean, damp, lint-free cloth.</p> <p>Previously varnished surface (without removing the old varnish): To clear a surface of the peeling off old varnish. Gently, without much effort, sand the entire surface with fine sandpaper (240). Remove dust. Do not prime surfaces previously varnished. Check the compatibility of the varnish with the old varnish by making a trial varnish in a small area.</p>
Application	<p>Mix the varnish before use and mix during application. To apply at a relative humidity of 40-70%, air temperature, base and varnish from + 15°C to + 25°C with a varnish roller or a varnish spatula. In small areas, a brush is possible. Application by roller (brush): 2-3 layers. Application with a spatula: 4-5 layers. To apply a varnish in the direction of incidence of light indoors or along wood fibers from edge to edge of a surface. Before applying the last coat of varnish, sand the surface with sandpaper (240), remove dust.</p> <p>Attention! Do not apply varnish in thick layers with excessive consumption of material. Applying varnish in direct sunlight, draft, dustiness of the room, increased (or lowered) temperature and humidity can lead to coating defects.</p>
Painted surface care	It is recommended that you clean the painted surface with a sponge or soft cloth using a warm detergent solution. The freshly painted surface should be handled carefully, since under normal conditions the coating reaches its final hardness after only 14 days. If it is necessary to clean the surface earlier than this period, it is recommended to lightly clean it with a soft damp cloth, avoiding rubbing.
Color	Milky beige. After drying, it is colorless.
Tinting	Varnish is not tinted. If necessary, tinting of the processed wood - tinting material must be applied to the prepared, polished surface before its priming. After the tinting material has dried, the surface should be carefully sanded, without applying great effort, with a fine sandpaper (240), removing the raised pile, but without damaging the main color layer of the material. Remove dust.
Consumption	Paint roller, brush (on one layer): 10-15 m ² / l. Spatula (on one layer): first layer up to 25 m ² / l, subsequent layers up to 50 m ² / l. To achieve maximum strength of the varnish coating, the total consumption of primer and varnish should be 3-5 m ² / l.
Drying time	Drying at a temperature of + 20°C and relative humidity of 65% at the recommended expense. From dust: 30 minutes. The next layer can be applied: when applied with a spatula - after 2 hours, when applied with a roller - after 4 hours. Grind the surface 6 hours after applying varnish. Light load (walking in soft shoes) - after 24 hours. Full load (furniture, carpets, etc.), wet cleaning - after 14 days.
Tools	Varnish roller, varnish spatula, brush.
Tool cleaning	Rinse immediately with water. Dry varnish is mechanically cleaned.
Composition	Polyurethane dispersion, water, additives.
Additional Information	

Frost resistance	Do not freeze during storage.
Warranty period of storage	24 months from the date indicated on the package.
Storage conditions	Store and transport in undamaged original hermetically sealed containers at temperatures from + 5°C to + 35°C. Do not expose to freezing and direct sunlight.
Precautionary measures	When working, follow the general rules of occupational health. Work in a well-ventilated area, in work clothes, gloves. Keep out of the reach of children. In case of contact with skin or eyes, rinse with water. The varnish is fire and explosion proof.
Disposal	Residues of dried varnish must be disposed of as household waste, polymer containers must be collected for recycling or disposal as household waste.
Volume / weight	0,75 L (0,77 Kg); 3 L (3,09 Kg); 5 L (5,15Kg)
<p>The information concerning the product is based on the results of laboratory tests and practical use of the product depending on the location and conditions of its use. As the manufacturer, we guarantee the quality of the product and provide the best recommendations for its appropriate application. As the manufacturer, we cannot control the conditions and circumstances of product transportation, storage and application and numerous other factors that affect its use. Thus, we shall not bear responsibility for the damage caused by ignoring the instructions for use or transportation, by noncompliance with storage conditions and timeframes or by inappropriate application of the product. The manufacturer reserves the right to alter product information at their discretion without prior notice. For additional information, please contact us: http://eskarо.ua/</p>	
Redaction Technical Specifications. № 01 dated 19/08/2019.	